

Thermally Conductive silicone pads TIF™ 200-01U Series



TIFTM200-01U Series thermally conductive interface materials are applied to fill the air gaps between the heating elements and the heat dissipation fins or the metal base.

Their flexibility and elasticity make them suited to the coating of the very uneven surfaces.

Heat can transmit to the metal housing or dissipation plate from the separate elements or even the entire PCB, which in effect enhances the efficiency and life-time of the heat-generating electronic components.

Features


- Naturally tacky needing no further adhesive coating
- Soft and Compressible for low stress applications
- Available in varies thickness


Application

- the chassis of frame
- » Car Battery & Power Supply
- » Charging Pile
- » Graphics Card Thermal Module
- Set Top Box
- » LED

Typical Properties of TIF200-01U Series					
Color	Gray / White	Visual	Dielectric Breakdown Voltage (T= 1mm above)	>5000 VAC	ASTM D149
Construction Reinforcement Carrier	Ceramic filled silicone elastomer TIS100 Series	******	Dielectric Constant	5.5 MHz	ASTM D150
Thermal Conductivity	1.25 W/mK	ASTM D5470	Volume Resistivity	4.0X10 ¹³ Ohm-meter	ASTM D257
Hardness	25 Shore 00	ASTM 2240	Continuous Use Temp	– 40 To 160 ℃	******
Specific Gravity	2.20 g/cc	ASTM D297	Outgassing (TML)	0.55%	ASTM E595
Thickness range	0.010"-0.200" (0.25mm-5.0mm)	ASTM D374	Flame Rating	94 V0	UL E331100

Product Identification:





Standard Thicknesses

0.010-inch to 0.200-inch (0.25mm to 5.0mm)

If you want to know our thermal Products, you can visit our website . http://www.ziitek.com

Gap Fillers | Pouring sealant | Silicon tape | Thermally Conductive paste | Flake graphite | Thermally Conductive Insulators | Ceramic heat sinks Thermally Conductive plastic | Thermally Conductive Adhesive Tapes

Canada:

Tel:+001-604-2998559 E-mail: sales@thermazig.com Taiwan:

Tel: +886-2-22771007 Fax: +886-2-22771075 E-mail: jerry@ziitek.com.tw Dongguan:

Tel: +86-769-38801208 Fax: +86-769-83791290 E-mail: angus@ziitek.com Kunshan:

Tel: +86-512-57816297 Fax: +86-512-57816327 E-mail: kelvin@ziitek.com Chengdu:

Tel: +86-28-62379168 Fax: +86-28-62379168 E-mail: david cd@ziitek.com